

Rulon® Chemical Resistance

Chemical	Rating
2 - butanone	A
Acetic acid	A
Acetylene	A
Alkalines	A
Ammonia	A
Amyl chloride	A
Aniline	A
Aqua Regia	A
Benzaldehyde or Benzonitrile	A
Benzenesulfonic Acid	A
Bromine	A
Calcium Hypochlorite	A
Camphor Oil or Carbon Sulfide	A
Carbon Tetrachloride	A
Chloral Hydrate or Chloroacetic Acid	A
Chlorine or Bleaching Agents	A
Chloroform or Chorosulfonic Acid	A
Chromic Acid	A
Concentrated Oxidizing Acids	A
Creosote or Cresol	A
Decalin or Dichlorobenzene	A
Diethyl Ether or Dimethylamine	A
Diemethyl Sulfoxide	A
Ethyl Acetate	A
Ethylene & Propylene Dichloride	A
Ferric Chloride	A
Ferric Nitrate	A
Ferric Sulfate	A
Ferrous Sulfate	A
Fluoboric Acid	A
Fluorinating Agents, Strong	NR
Fluorine > 140°F & Dry Gas > 250°F	NR
Fluosilicic Acid	A
Hydrobromic Acid	A

Chemical	Rating
Hydrochloric Acid	A
Hydrocyanic Acid	A
Hydrofluoric Acid	A
Hydrofluosilicic Acid	A
Hydrogen Fluoride, Dry > 250°F	NR
Hydrogen Peroxide	A
Hydrogen Sulfide, Moist	A
Hydroxides	A
Mercury or Silver Salts	A
Methyl Chloride or MEK	A
Molten Alkali Metals	NR
Molten Anhydrous Bases	NR
Nitric Acid	A
Nitro Benzene	A
Oleum	A
P-dioxane or Phenol	A
Partly Halogenated Hydrocarbons	A
Phosphoric Acid	A
Potassium Chlorate	A
Potassium or Sodium Cyanide	A
Potassium Dichromate or Nitrate	A
Potassium Hydroxide	A
Sodium Chlorate	A
Sodium Hydroxide	A
Sodium Nitrate	A
Stannous Chloride	A
Sulfur Dioxide 5% + H ₂ O	A
Sulfur Molten	A
Sulfuric Acid	A
Tetralin or Trichlorethylene	A
Toluene	A
Trifluoroacetic Acid	A
Xylene	A
Zinc Chloride	A



A = ACCEPTABLE

NR = NOT RECOMMENDED

Important Note:

This chart is intended to provide general information only; there are exceptions for some Rulon grades. We recommend that you check with [TriStar engineering](http://www.tristar-engineering.com) as some fillers can be attacked in certain chemical conditions.

General Warranty Information:

All information contained herein is believed to be correct but is presented without any guarantee, warranty or representation of any kind, express or implied. Technical data set forth herein is based on tests and measurements conducted in our laboratory under controlled conditions. Suggestions concerning possible applications of our products are made without representation or warranty that such use is free from patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other such measures may not be required.

We're ready to put our engineering expertise to work for you from prototype to production.

Engineering | Custom Fabrication | Manufacturing

CJ Composite

- Self-Lubricating
- Low weight | High Strength
- Chemical Resistance
- Direct replacement for Bronze



Ultracomp®

- Self-Lubricating
- High Load | Low Speed
- High Compressive Strength
- Vibration & Impact Resistance



TriSteel™

- Self-Lubricating
- High Load | High Speed
- Metal Backed Bearing System
- 100% Lead Free



Rulon®

- Self-Lubricating
- Low weight | High Strength
- Low Coefficient of Friction
- Chemically Resistant




Meldin®

- High Performance Materials
- High Temp Dimensional Stability
- Chemical Resistance
- Withstands Thermal Shocks



Enhanced Materials

- Plasma Surface Treatment
- Filtration Membranes
- Specialized Primers & Coatings
- Material ID & Selection




©TriStar Plastics Corp. All rights reserved.
Ultracomp® is a registered trademark
and TriSteel™ is a trademark of TriStar Plastics Corp.

Rulon® and Meldin® are registered trademarks of
Saint-Gobain Performance Plastics Corporation.