

MATERIAL DATASHEET

Meldin® 5301 Types III-IX

Features: Beige, Proprietary custom PEEK, Type IX qualified according to NORSOK M710 rev3 up to 15% H2S – Temperature class X

Benefits: Wide chemical resistance and Good mechanical properties at elevated temperatures

Working Temperature Range: -80° to +260°C [-112° to +500°F]

Properties	Test Methods	Typical Values	Units
PHYSICAL			
Specific Gravity	ASTM D792	1,31	--
Water Absorption, 24hr	ASTM D570	0,5	%
MECHANICAL			
Tensile Strength-RT- Yield	ASTM D638	92 [13,300]	MPa [psi]
Elongation-RT Break	ASTM D638	16	%
Tensile Modulus-RT	ASTM D638	NA	GPa [psi x 10 ⁵]
Compressive Strength – RT	ASTM D695	118 [17,100]	MPa [psi]
Compressive Modulus-RT	ASTM D695	NA	GPa [psi x 10 ⁵]
Flexural strength-RT	ASTM D790	170 [24,700]	MPa [psi]
Flexural Modulus-RT	ASTM D790	NA	GPa [psi x 10 ⁵]
THERMAL			
Melting point	ASTM D3418	343 [650]	°C [°F]
Glass Transition Temperature	ASTM D3418	143 [290]	°C [°F]
Linear Coefficient of Thermal Expansion along flow, <Tg / >Tg	ASTM E831	4.7 [2.6] / NA	m/m/°C [in/in/°F] x 10 ⁻⁵
Linear Coefficient of Thermal Expansion average, <Tg / > Tg	ASTM E831	NA	m/m/°C [in/in/°F] x 10 ⁻⁵
Thermal conductivity	ASTM F433	NA	GPa [psi x 10 ⁵]
Heat deflection temperature	ASTM D648	NA	°C [°F]
ELECTRICAL			
Dielectric Strength (2.5 mm thick)	ASTM D149	16 [407]	kV/m [V/mil]
Dielectric Constant-RT, 1kHz)	ASTM D150	3.1	-
Volume Resistivity-RT	ASTM D257	10 ¹⁶	Ohm cm

The table above represents typical values, intended for reference only. They should NOT be used as a basis for design specifications or quality control. Meldin® is a registered trademark. © 2021 Omniseal Solutions™